

COMPUTATIONAL STUDY ON SHEAR STRENGTHENING OF RC CONTINUOUS BEAMS USING CFRP SHEET

NABIL MOHAMED EMHDAB ALNATIT

A thesis is submitted of the fulfillment of the requirements
for the award of the degree of Master of Civil
Engineering

Faculty of Civil and Environmental Engineering
University Tun Hussein Onn Malaysia (UTHM)

MAY.. 2011



PTTA UTHM
PERPUSTAKAAN TUNKU TUN AMINAH

Especially dedicated to:

For my Father, Mother and brother

Words cannot express everything you have done for me ... thank you so much

For all of my support to achieve this research. My wife, sisters, friends and all those

Who have been a great

Help in the completion of this thesis

My love for you all remains forever...



PTTA UTHM
PERPUSTAKAAN TUNKU TUN AMINAH

Acknowledgements



First and foremost, thanks are to Almighty Allah, the creator, the cherisher, the most wise, the all knowing, the lord of the world, the master of the universe and the sustainer of life under whose protection and guidance I was able to fulfill this task. Certainly Allah's assistance has been the most important not only for the successful completion of this thesis but for my entire life as a whole and the hereafter. Full appreciations of them are not enough words of thanks, my mother, and my family.

I would like to extend my sincere thanks and appreciation to my supervisor, Prof DR Abdul Aziz Abdul Samad, for invaluable encouragement and guidance during the preparation of this thesis. Lastly, a million thank you to all persons and individuals who have been involved towards the completion of this project whether directly or indirectly.



PTTA
PERPUSTAKAAN TUNKU ABDUL RAHMAN

ABSTRACT

This research studied the feasibility and effectiveness of a new method of strengthening existing RC continuous beams in shear by using CFRP strips. The CFRP composite strips were used to strengthen concrete externally at a known failure plane to resist shear stresses in shear friction. All beams were design to fails in shear with a_v/d 2.5. This research describes the computational study on shear strengthening of RC continuous beams using CFRP strips. In this study, a computational program consisting of 5 beams were performed subjected to experimental program with the same size and details of the beams where the experimental study was performed by other student in the laboratory. Here in this part the study done through simulation by ABAQUS Software version 6.9. Therefore, this research aims to investigate the effectiveness of using externally bonded CFRP strips in repair and strengthen of RC continuous beams and also to know the behavior of RC continuous beams strengthened in shear with CFRP sheet. So in this study there are five specimens with different CFRP wrapping scheme as 90 degree and 45 degree with three sides and four sides each beam. The computational results were compare with the experimental results that obtained by other student. The computational results show great agreement with the experimental results.

ABSTRAK

Kajian ini dijalankan bagi mengkaji keberkesanan kaedah baru bagi pengukuhan ricih rasuk selangar konkrit bertetulang yang sedia ada menggunakan lajur-lajur CFRP. Lajur-lajur CFRP digunakan untuk pengukuhan concrete secara luaran untuk menahan tegasan ricih. Kesemua rasuk direkabentuk untuk gagal dalam ricih dengan av/d 2.5. Kajian ini menerangkan kajian simulasi terhadap pengukuhan ricih bagi rasuk selangar konkrit bertetulang menggunakan lajur-lajur CFRP. Dalam kajian ini, program simulasi terhadap lima rasuk selangar telah dijalankan dimana rasuk-rasuk tersebut adalah sama saiz dan berpandukan kepada kajian makmal yang telah dijalankan oleh pelajar lain. Kajian ini dijalankan dengan menggunakan simulasi computer ABAQUS versi 6.9. Kajian ini dijalankan bagi menyiasat keberkesanan pengukuhan secara luaran menggunakan lajur-lajur CFRP terhadap rasuk selangar konkrit bertetulang disamping untuk mengenalpasti kelakuan rasuk selangar konkrit bertetulang yang diperkukuhkan menggunakan lajur-lajur CFRP. Oleh itu, terdapat lima rasuk terlibat dimana setiap satunya berbeza daripada orientasi lajur-lajur CFRP iaitu sama ada 45 darjah atau 90 darjah dan juga berbeza dari segi sama ada dibalut empat sisi atau tiga sisi. Kajian simulasi kemudiannya dibandingkan dengan kajian makmal yang telah dijalankan oleh pelajar lain. Kajian simulasi didapati menunjukkan hasil yang memuaskan setelah dibandingkan dengan kajian makmal.

CONTENTS

TITLE	I	
DEDICATION	II	
ACKNOWLEDGEMENT	III	
ABSTRACT	IV	
ABSTRAK	V	
CONTENTS	VI	
LIST OF TABLES	XI	
LIST OF FIGURES	XII	
CHAPTER 1 INTRODUCTION		
1.1	Introduction	1
1.2	Problem Statement	2
1.3	Objectives of Project	2
1.4	Scope of Project	3
1.5	Significance of Research	3

CHAPTER 2 LITERATURE REVIEW

2.1	Introduction of FRP	4
2.2	Fiber reinforced polymer	5
2.2.1	History of FRP	5
2.2.2	Definition of FRP	7
2.2.3	Types of CFRP	8
2.2.4	The uses of FRP	9
2.2.5	Advantages of FRP	10
2.2.6	Disadvantages of FRP	12
2.3	Shares strength of reinforced concrete using FRP	12
2.3.1	The equation used to calculate shear strength	13
2.3.1.1	ACI Code provisions for shear strength of Beams	13
2.3.1.2	Khalifa Equation	14
2.4	Finite element analysis	16
6.2	Conclusion	17

CHAPTER 3 RESEARCH METHODOLOGY

3.1	Introduction	18
3.2	Beam details	18
3.3	Materials of the beams	21
3.4	Abaqus software	22
3.4.1	Introduction to Abaqus/CAE	22
3.4.2	Starting Abaqus	23

3.4.3.1	Components of the main window	24
3.4.4	Systems support	25
3.4.5	Exiting an ABAQUS/CAE session	25
3.4.6	ABAQUS Finite Element System	25
3.4.7	Finite Element Meshes	26
3.4.8	Material modeling	29
3.4.9	Boundary condition	29
3.4.10	Analysis Running and Results	30

CHAPTER 4 RESULTS AND DISCUSSION

4.1	Introduction	32
4.2	Ultimate load	32
4.3	Load Displacement Behavior	33
4.3.1	Comparison between simulation and experimental study	34
4.3.1.1	Comparison between simulation and experimental for C2.5-C	34
4.3.1.2	Comparison between simulation and experimental for C2.5- UA-S	35
4.3.1.3	Comparison between simulation and experimental for C2.5-U-S	36
4.3.1.4	Comparison between simulation and experimental for C2.5-LA-S	37
4.3.1.5	Comparison between simulation and experimental for C2.5-L-S	38
4.4	Load - Main Reinforcement Strain	39
4.4.1	Comparison between simulation and experimental for C2.5-C	40
4.4.2	Comparison between simulation and experimental for C2.5-UA-S	41
4.4.3	Comparison between simulation and experimental for C2.5-U-S	42

4.4.4	Comparison between simulation and experimental for C2.5-LA-S	43
4.4.5	Comparison between simulation and experimental for C2.5-L-S	44
4.5	Load – strain results	45
4.5.1	Load – stirrups strain	45
4.5.1.1	Load-Stirrups Strain Behavior of C2.5-C, (S1, S2, S3, and S4)	45
4.5.1.2	Load-Stirrups Strain Behavior of C2.5-UA-S, (S1, S2, S3, and S4)	47
4.5.1.3	Load-Stirrups Strain Behavior of C2.5-U-S, (S1, S2, S3, and S4)	49
4.5.1.4	Load-Stirrups Strain Behavior of C2.5-LA-S, (S1, S2, S3 and S4)	51
4.5.1.5	Load-Stirrups Strain Behavior of C2.5-L-S, (S1, S2, S3, and S4)	53
4.5.2	Load - concrete surface strain	55
4.5.2.1	Load-Concrete Surface Behavior of C2.5-C for (C1, C2, C3 and C4)	56
4.5.2.2	Load-Concrete Surface Behavior of C2.5-UA-S for (C1, C2, C3 and C2)	58
4.5.2.3	Load-Concrete Surface Behavior of C2.5-U-S for (C1, C2, C3 and C4)	60
4.5.2.4	Load-Concrete Surface Behavior of C2.5-LA-S for (C1, C2, C3 and C4)	62
4.5.2.5	Load-Concrete Surface Behavior of C2.5-L-S for (C1, C2, C3 and C4)	64
4.5.3	Load – CFRP strain	66
4.5.3.1	Load CFRP Behavior of C2.5-UA-S for (F1, F2, F3 and F4)	66
4.5.3.2	Load CFRP Behavior of C2.5-U-S for (F1, F2, F3 and F4)	68
4.5.3.3	Load CFRP Behavior of C2.5-LA-S for (F1, F2, F3, and F4)	70
4.5.3.4	Load CFRP Behavior of C2.5-L-S for (F1, F2, F3, and F4)	72

CHAPTER 5 CONCLUSIONS AND RECOMMENDATIONS

5.1	Introduction	74
5.2	Conclusion	74
5.3	Recommendation	75
	REFERENCE	76
	APPENDIX	79



LIST OF TABLES

Table 3.1:	Information of all beams	19
Table 3.2:	Properties of Sikadur-330 (Sika kimia, 2009)	21
Table 4.1:	The ultimate load for all specimen	32
Table 4.2:	The displacement for C2.5-C	34
Table 4.3:	The displacement for C2.5-UA-S	35
Table 4.4:	The displacement for C2.5-U-S	36
Table 4.5:	The displacement for C2.5-LA-S	37
Table 4.6:	The displacement for C2.5-L-S	38
Table 4.6:	The Reinforcement for C2.5-C	40
Table 4.7:	Load – Main Reinforcement Strain for C2.5-UA-S	41
Table 4.8:	Load – Main Reinforcement Strain for C2.5-U-S	42
Table 4.9:	Load – Main Reinforcement Strain for C2.5-LA-S	43
Table 4.10:	Load – Main Reinforcement Strain for C2.5-L-S	44

LIST OF FIGURES

Figure 2.1:	Comparison among CFRP, AFRP, and GFRP sheets and reinforcing steel in terms of stress-strain relationship	8
Figure 3.1:	Reinforcement	19
Figure 3.2:	Cross section details	20
Figure 3.3:	Loading Position	20
Figure 3.4:	Cross Section for Fully Wrap (4 sides bonding)	20
Figure 3.5:	Cross Section for 3 Sides Bonding	21
Figure 3.6:	Preprocessing, simulation, and processing	22
Figure 3.7:	Components that appear in the main window	24
Figure 3.8:	The size of mesh for the concrete beam	27
Figure 3.9:	Concrete beam after mesh	27
Figure 3.10:	Stirrup after mesh	28
Figure 3.11:	Main steel reinforcement after mesh	28
Figure 3.12:	Material of concrete	29
Figure 3.13:	Boundary condition and load	30
Figure 3.14:	Step on submit and getting results	30
Figure 3.15:	Project flow chart	30
Figure 4.1:	Load – displacement for all beams	33
Figure 4.2:	Load displacement for C2.5-C	34
Figure 4.3:	Load displacement for C2.5-UA-S	35
Figure 4.4:	Load displacement for C2.5-U-S	36
Figure 4.5:	Load displacement for C2.5-LA-S	37

Figure 4.7:	Load - Main Reinforcement Strain for all beams	39
Figure 4.8:	Load – Main Reinforcement Strain for C2.5-C	40
Figure 4.9:	Load – Main Reinforcement Strain for C2.5-UA-S	41
Figure 4.10:	Load – Main Reinforcement Strain for C2.5-U-S	42
Figure 4.11:	Load – Main Reinforcement Strain for C2.5-LA-S	43
Figure 4.12:	Load – Main Reinforcement Strain for C2.5-L-S	44
Figure 4.13:	Load – Stirrups Strain Behavior	45
Figure 4.14:	Load – stirrups strain for C2.5-C	46
Figure 4.15:	Load – Stirrups Strain Behavior	47
Figure 4.16:	Load – stirrups strain for C2.5-UA-S	48
Figure 4.17:	Load – Stirrups Strain Behavior	49
Figure 4.18:	Load – stirrups strain for C2.5-U-S	50
Figure 4.19:	Load – Stirrups Strain Behavior	51
Figure 4.20:	Load – stirrups strain for C2.5-LA-S	52
Figure 4.21:	Load – Stirrups Strain Behavior	53
Figure 4.22:	Load – stirrups strain for C2.5-L-S	54
Figure 4.23:	Load - concrete surface strain	56
Figure 4.24:	Load – concrete surface strain for beam C2.5-C	57
Figure 4.25:	Load - concrete surface strain	58
Figure 4.26:	Load – concrete surface strain for beam C2.5-UA-S	59

Figure 4.27:	Load - concrete surface strain	60
Figure 4.28:	Load – concrete surface strain for beam C2.5-U-S	61
Figure 4.29:	Load - concrete surface strain	62
Figure 4.30:	Load – concrete surface strain for beam C2.5-LA-S	63
Figure 4.31:	Load - concrete surface strain	64
Figure 4.32:	Load – concrete surface strain for beam C2.5-L-S	65
Figure 4.33:	Load – CFRP strain of C2.5-UA-S for (F1, F2, F3 and F4)	66
Figure 4.34:	Comparison among simulation and experimental Load – CFRP strain for beam C2.5-UA-S	67
Figure 4.35:	Load – CFRP strain of C2.5-U-S for (F1, F2, F3 and F4)	68
Figure 4.36:	Comparison among simulation and experimental Load – CFRP strain of C2.5-U-S	69
Figure 4.37:	Load – CFRP strain of C2.5-LA-S for (F1, F2, F3, and F4)	70
Figure 4.38:	Comparison among simulation and experimental Load – CFRP strain of C2.5-LA-S	71
Figure 4.39:	Load – CFRP strain C2.5-L-S for (F1, F2, F3, and F4)	72
Figure 4.40:	Comparison among simulation and experimental Load – CFRP strain C2.5-L-S	73

CHAPTER 1

1.1 Introduction

During the past 30 years, it has been necessary to strengthen increasing numbers of reinforced concrete beams. In the early days, this was achieved by bonding thin steel plates to beam soffits or sides to enhance the flexural or shear strength. However, steel has numerous disadvantages, the most obvious of which is its great weight. In the late 1980s, this material began to be replaced by carbon fiber-reinforced polymer (CFRP) plates which were much lighter and stronger than steel.

The majority of early investigations into (CFRP) were directed at flexural strengthening and little research was undertaken into the use of CFRP for shear strengthening. However, the publication of Concrete Society Technical Report 55 Design guidance for strengthening concrete structures using fiber composite materials briefly describes some applications and provides design guidance on the use of fiber composites to enhance shear strength.

This study covers the computational study on shear strengthening of reinforced concrete continuous beams using CFRP sheet and tends to reduce the problems regarding shear failure and a sudden collapse of a structure.

1.2 Problem statement

Shear failure of reinforced concrete (RC) is very dangerous and occurs suddenly with no advance warning. Therefore, it is important to understand the behavior of shear of

reinforced concrete continuous beams. This includes the behavior of the beam before and after crack. Traditionally, repair of reinforced concrete is done by using steel plate as the external strengthened mechanism. However, steel plate shows weaknesses in terms of corrosion of the steel plate due to the environment. Therefore, this study tends to use CFRP as it has better performance in terms of the reaction with the environment compared with steel plate. In this study, a computational program consisting of 5 beams will be performed subjected to experimental program with the same size and details of the beams where the experimental study was performed by other student. The CFRP composite strips were used to strengthen concrete externally at a known failure plane to resist shear stresses in shear friction. All beams were design to fails in shear with a_v/d 2.5. This paper describes the computational study on shear strengthening of RC continuous beams using CFRP sheet.

1.3 Objectives of project:

- 1) To investigate the effectiveness of using externally bonded CFRP strips in repair and strengthen of RC continuous beams.
- 2) To study the behavior of RC continuous beams strengthened in shear with CFRP sheet using finite element analysis.
- 3) To investigate the shear behavior of RC continuous beams repair with different CFRP wrapping scheme.

1.4 Scope of project

- 1) This study involves a finite element modeling and analysis of RC continuous beams externally strengthened with CFRP sheet.
- 2) Computational study using ABAQUS software.

- 3) The results from finite element analysis using ABAQUS software will be compared with laboratory results which performed by another student.
- 4) The CFRP wrapping scheme will involve wrapping four sides and wrapping three sides of the beams.
- 5) All beams were designed to fails in shear with a_v/d 2.5.

1.5 Significance of Research

The importance of this research is it aims to contribute on the study of shear strengthening of RC continuous beams using Carbon Fiber Reinforced Polymer (CFRP) to increase the shear capacity of the beams. This study will also investigate the behavior of reinforced concrete continuous beams strengthened in shear with CFRP sheet by using finite element analysis. Finite element analysis (FEA) can analyze the design in detail, saving time and money by reducing the number of prototype required.

CHAPTER 2

2.1 Introduction of FRP

There are considerable numbers of existing reinforced concrete structures in world that do not meet current design standards, because of inadequate design and/or construction error or need structural upgrading to meet new seismic design requirements. Retrofitting of flexural concrete elements is traditionally accomplished by externally bonding steel plates to concrete. Although this technique has proved to be effective in increasing strength and stiffness of reinforced concrete elements, yet it has the disadvantages of being susceptible to corrosion and difficult to application and installation. Recent development in the field of composite materials, together with their inherent properties, which include high specific tensile strength, good fatigue and corrosion resistance and ease of use, make them an attractive alternative to steel plates in the field of repair and strengthening of concrete elements.

The use of fiber reinforced polymer (FRP) composites for strengthening reinforced concrete(RC) structure was first investigated as an alternative to steel plate bonding for beam strengthening at the Swiss Federal Laboratory for Materials Testing and Research (EMPA) (Meier et al. 1993) where tests on RC beams strengthened with CFRP plates started in 1984.

After this many research studies have been carried out and awareness, trust and confidence on FRP composites increased among the professionals particularly in USA, Japan and the countries of Europe. Today they are many case studies in these countries where this technique has achieved desired results. Corrosion of steel reinforcement embedded in concrete structures is considered to be the main cause of structural concrete deterioration. Chloride ions produced by the corrosion of the steel reinforcement can

cause serious damage to surrounding concrete and also depreciate the strength of the corroded member. In many regions the corrosion of the steel reinforcement is accelerated by the use of deicing salts and other chemicals to prevent freezing. Many various approaches have been attempted to control the corrosion of the reinforcing steel: epoxy coated rebar; protection increased cover use of polymer concretes etc. However, none of these approaches provides a permanent solution as they all still incorporate the usage of corrosive steel. Recently advances in fiber reinforced plastics (FRP) have made replacing steel reinforcement with non-corrosive FRP's a viable alternative.

CFRP's offer many advantages as compared to steel reinforcement including high strength to weight ratio, excellent fatigue characteristics, corrosion resistance, electromagnetic neutrality, low axial coefficient of thermal expansion, and handle ability due to its light weight.

2.2 Fiber reinforced polymer

2.2.1 History of FRP

FRP composites are the latest version of the very old idea of making better composite material by combining two different materials that can be traced back to the use of straw as reinforcement in bricks used by ancient civilizations (e.g. Egyptians in 800). The development of FRP reinforcement can be found in the expanded use of composites after World War II: the automotive industry first introduced composites in early 1950's and since then many components of today's vehicles are being made out of composites. The aerospace industry began to use FRP composites as lightweight material with acceptable strength and stiffness which reduced the weight of aircraft structures such as pressure vessels and containers. Today's modern jets use large components made out of composites as they are less susceptible to fatigue than traditional metals. Other industries

like naval, defense and sporting goods have used advanced composite materials on a widespread basis: pultrusion offered a fast and economical method of forming constant profile parts, and pultruded composites were being used to make golf clubs and fishing poles. Only in the 1960s, however, these materials were seriously considered for use as reinforcement in concrete.

More recently, EOCRETE has headed the European effort with research and demonstration projects. In Japan more than 100 commercial projects involving FRP reinforcement were undertaken up to the mid-1990s (ACI Committee 440, 2001). The 1980s market demanded nonmetallic reinforcement for specific advanced technology; the largest demand for electrically nonconductive reinforcement was in facilities for MRI (Magnetic Resonance Imager) medical equipment. FRP reinforcement became the standard in this type of construction. Other uses developed as the advantages of FRP reinforcement became better known and desired, specifically in seawall construction, substation reactor bases, airport runways, and electronics laboratories (Brown and Bartholomew 1996).

2.2.2 Definition of FRP

FRP composites consist of high strength fibers embedded in a polymer resin. The fibers are the main load-carrying element and have a wide range of strengths and stiffnesses with a linear stress-strain relationship up to failure. Fiber types typically used in the fabrication of FRP composites for construction are carbon, glass, and aramid. All these fibers are available commercially as continuous filaments.

The polymer resin surrounds and encapsulates the fibers to bind them together, protect them from damage, maintain their alignment, and allow distribution of load among them. Polymers are available as two categories; thermosetting polymers (e.g. epoxy and polyester) and thermoplastic polymers (e.g. nylon).

FRP composites have become more popular and accepted by designers, contractors, and owners due to combinations of their unique characteristics. FRP

composites have significantly higher strength-to-weight ratio than metals and other construction materials. In addition, these materials are non-corrosive, non-magnetic, and generally resistant to chemicals. A comparison among carbon FRP, aramid FRP (AFRP), and glass FRP (GFRP) sheets (based on fiber area only), and reinforcing steel in terms of stress strain relationship is illustrated in next figure




Figure .2.1: Comparison among CFRP, AFRP, and GFRP sheets and reinforcing steel in terms of stress-strain relationship.

2.2.3 Types of CFRP

There are three types of CFRP

GFRP - Glass fibers typically have a Young modulus of elasticity (70 GPa for E-glass) lower than carbon or aramid fibers and their abrasion resistance is relatively poor. In addition, a glass fiber has low fatigue strength. To enhance the bond between fibers and matrix, as well as to protect the fibers and moisture, fibers undergo sizing treatments acting as coupling. Such treatments are useful to enhance durability and fatigue

performance (static and dynamic) of the composite material. FRP composites based on fiberglass are usually denoted as GFRP.

AFRP – Aramid fibers are organic fibers, made of aromatic polyamides in an extremely orient form. Due to the anisotropy of the fiber structure, compression loads promote a localized yielding of the fibers resulting in fiber instability and formation of kinks. Aramid fibers may degrade after extensive exposure to sunlight, losing up to 50 % of their tensile strength. In addition, they may be sensitive to moisture. Their creep behavior is similar to that of glass fibers, even though their failure strength and fatigue behavior is higher than GFRP. FRP composites based on aramid fibers are usually denoted as CFRP. For strengthening purposes in civil engineering carbon fibers are the most suitable.

CFRP - Carbon fibers are used for their high performance and are characterized by high Young modulus of elasticity as well as high strength. They have an intrinsically brittle failure behavior with a relatively low energy absorption; nevertheless, their failure strength are larger compared to glass and aramid fibers. Carbon fibers are less sensitive to creep rupture and fatigue and show a slight reduction of the long-term tensile strength. FRP composites based on carbon fibers are usually denoted as CFRP.

2.2.4 The uses of FRP

FRP composites can be produced by different manufacturing methods in many shapes and forms. The most popular ones for concrete reinforcement are bars, prestressing tendons, pre cured laminates shells, and fiber sheets. FRP bars and tendons are currently produced with sizes and deformation patterns similar of those of steel bars, strands and solid wires.

They are commonly used for internal concrete reinforcement. FRP pre-cured laminates shells and sheets are commonly used as external reinforcement for repair and strengthening purposes. Here are some common uses in the field of engineering:

- 1) To resolve corrosion problems in reinforcing steel
- 2) To increase the efficiency of repair work for the deteriorating RC infrastructure, professionals have turned to alternative materials such as FRP composites.
- 3) The interest in the use of composites is attributable to declining manufacturing costs combined with ease and speed of installation.

The structural design and thus the production of structural elements made of reinforced concrete is based on forces and loads current in codes of the time. However, during the service life of a structure, various circumstances may require that the service loads are changed due to:

- 1) A modification of the structure: cutting of holes in slabs or beams.
- 2) A different use of the structures: from offices to library.
- 3) Ageing of the construction materials.
- 4) Deterioration of the concrete caused by reinforcement corrosion.
- 5) Cutting of pre- or post- stressed reinforcement cables.
- 6) Fire damages.
- 7) Upgrading of building codes.
- 8) Earthquake design requirements.

The CFRP laminates are used for the post-strengthening of structures to increase the load bearing capacity of structural components (increase of bending tensile force). The increased flexural capacity results in reduced deflections and the reduction in crack propagation. The use of carbon fiber plate has distinct advantages over the use of conventional steel plate and provides the designer with a unique freedom of design. Carbon fiber plates can be applied to both wooden and concrete beams, columns, slabs and walls for permanent structural reinforcement. This is in both the positive as well as negative moment.

2.2.5 Advantages and disadvantages of FRP

Advantages of FRP reinforcement:

- 1) High longitudinal tensile strength (varies with sign and direction of loading relative to fibers)
- 2) Corrosion resistance (not dependent on a coating)
- 3) Nonmagnetic
- 4) High fatigue endurance (varies with type of reinforcing fiber)
- 5) Lightweight (about 1/5 to 1/4 the density of steel)
- 6) Low thermal and electric conductivity (for glass and aramid fibers)

Weight advantages

another very distinct advantage of FRP is its low weight to strength ratio as a rule of thumb for the same strength FRP will weigh approximately one seventh as much as steel, and half as much as aluminum. Light weight properties are important when considering the cost and ease of installation especially for pipe and tanks. FRP's inherent light weight is an advantage when equipment must be mounted on existing structures such as scrubbers on mezzanines applications such as FRP tank trailers.

High Strength

While not as important for corrosion resistant equipment, high strength does play a major role in the design of FRP equipment for such applications as missiles, pultruded shapes, etc. for filament wound pipe and duct, the high strength gives the light weight features discussed earlier. You will often see FRP equipment, especially filament wound equipment, advertised as stronger than steel for pressure application, FRP's high strength properties can be a major advantage.

References

Adhikary, B. B., & Mutsuyoshi, H. _2004_. “*Behavior of concrete beams strengthened in shear with carbon-fiber sheets.*” *J. Compos.Constr.*, 8_3_, 258–264.

Ahmed Mahmud Khalifa. (March 1999).*Shear performance of reinforced concrete beams Strengthened with advanced composites.*

Al-Sulaimani, G. J., Istem, A., Basunbul, A. S., Baluch, M. H., & Ghaleb, B. N._1994_. “*Shear repair for reinforced concrete by fiberglass plate bonding.*” *ACI Struct.J.*, 91_3_, 458–464.

Alex Li,¹ Jules Assih,² & Yves delmas³ (April 2001).*shear strengthening of rc beams with externally bonded CFRP sheets.*

Bousselham, A., & Chaallal, O. _2004_. “*Shear strengthening reinforced concrete beams with fiber-reinforced polymer: Assessment of influencing parameters and required research.*” *ACI Struct. J.*, 101_2_, 219–227.

Bousselham, A., & Chaallal, O. _2004_. “*Retrofit of reinforced concrete T-beams in shear with U-shaped CFRP wrap.*” *Proc., 4th Int. Symp. On Advanced Composite Materials in Bridges and Structures, Canadian Society for Civil Engineering _CSCE_, Calgary, Alta., 8.*

Professor Carlo Pellegrino (June 2009).*Flexural Strengthening of Reinforced Concrete Beams with Prestressed FRP.*

Chu kia Wang. (1998).*sixth edition. reinforced concrete design.*

Gamage, J.C.P.h, wong, M.B & Al mahidi R. (2005).*Performance of CFRP strengthened concrete members under elevated temperatures.*

Godat, A., Neale, K. W., & Labossière, P. _2007b_. “Towards modeling FRP shear-strengthened reinforced concrete beams.” *Proc., 8th Int. Symp. on Fiber Reinforced Polymer Reinforcement for Concrete Structures, University of Patras, Patras.*

Hsuan-Teh Hu *, Fu-Ming Lin, Yih-Yuan Jan (2004). *Nonlinear finite element analysis of reinforced concrete beams strengthened by fiber-reinforced plastics*

H. K. Lee†, S. K. Ha *et al* (2008). *Finite element analysis of shear-deficient RC beams strengthened with CFRP strips/sheets.*

Jayabrakash, (August 2006). *Shear strengthening of reinforced concrete beams using externally bonded BI- directional carbon fiber reinforced polymer.*

Khalifa, A., & Nanni, A. _2000_. “Improving shear capacity of existing RC T-section beams using CFRP composites.” *Cem. Concr. Compos.*, 22_3_, 165–174.

Leung, C., Chen, Z., Lee, S., Ng, M., Xu, M., and Tang, J. _2007_. “Effect of size on the failure of geometrically similar concrete beams strengthened in shear with FRP strips.” *J. Compos. Constr.*, 11_5_, 487–496.

Liu Zihong, (July 2007). *Testing and analysis of a fiber reinforced polymer”.*

Mohamed Sh Mahmud (2009). *Finite Element Modeling Reinforced Concrete Beams Strengthened with FRP Laminates.*

Nabil F. Grace (May-June 2001). *Strengthening of negative moment region of reinforced concrete beams using carbon fiber- reinforced polymer strips.*

Santhakumar, R., Chandrasekaran, E., & Dhanarraj, R. _2004_. “*Analysis of retrofitted reinforced concrete shear beams using carbon fiber composites.*” *Electron. J. Struct. Eng.*, 4, 66–74.

Shahawy, M., & Beitelman, T. E. ~2000!. “*Static and fatigue performance of RC beams strengthened with CFRP laminates.*” Rep., Structural Research Center, Florida Dept. of Transportation, Tallahassee, Fla.

Triantafillou, T. C. _1998_. “*Shear strengthening of reinforced concrete beams using epoxy-bonded FRP composites.*” *ACI Struct. J.*, 95_2_, 107–115.

Wong, R. _2001_. “*Towards modeling of reinforced concrete members with externally bonded fiber reinforced polymer _FRP_ composites.*” MS thesis, Univ. of Toronto, Toronto, Ont.

ACI 440.2R, 2008, “*Guide for the Design & Construction of Externally Bonded FRP Systems for Strengthening of Concrete Structures,*” American Concrete Institute.

